











	PROPERTY	TEST METHOD	3200mmx 1600mm
	Surface Quality	GB/T3810.2-2016	100%
	Water Absorbtion	GB/T3810.3-2016	0.08%
	Chemical Resistance	GB/T3810.13-2016	Grade GA (resistant)
	Stain Resistance	GB/T3810.14-2016	Class 5 (resistant)
	Impact Resistance (COR)	GB/T3810.5-2016	0.87 (resistant)
	Abrasion Resistance	GB/T3810.7-2016	Class 4 (resistant)
	Thermal Expansion	GB/T3810.7-2016	$6.0 \times 10^{-6} \text{ C}^{-1}$
	Thermal Shock Resistant	GB/T3810.7-2016	Fully resistant
	Frost Resistant	GB/T3810.12-2016	Fully resistant
	Static Co-efficient of friction	Annex M	0.51 ~0.52

Branches: JHB DBN CPT

www.estrellasasa.co.za

